



## PRODUCT DESCRIPTION

Crush is a luxurious, trowelled mortar that utilizes a mix of natural aggregates, bound in resin, to create an earthy, yet sophisticated floor. Crush draws from nature, bringing the outside in.

## USES, APPLICATIONS

Crush is specifically designed for public areas that will see heavy foot traffic. The sealed surface resists scratching and is easy to clean.

Crush is ideal for applications such as: retail, hospitality, casinos, showrooms, lobbies, restaurants, nightclubs, commercial, and public spaces.

## SUBSTRATE

Crush, with the appropriate primer, is suitable for application over concrete, wood or metal. Not recommended on asphalt, brick, quarry tile, mastic, or painted surfaces. These must first be removed by mechanical means to expose the substrate prior to priming and overlayment.

## SYSTEM OPTIONS

### *Moisture Barrier*

To ensure long-term adhesion to concrete slabs in the absence of a proper vapor barrier, liquid elements offers systems to protect against moisture vapor transmission in the substrate.

## MATTE FINISH

Stonseal CF7 is available and provides a high performance, UV stable, matte finish.

## THICKNESS

Crush can be installed at various thickness, depending on the type and grade of aggregate chosen.

## STORAGE CONDITIONS

Store all components of Crush between 65 to 85°F/18 to 30°C in a dry area. Avoid excessive heat and do not freeze. The shelf life is 3 years in the original, unopened container.

## PHYSICAL CHARACTERISTICS

Compressive Strength (ASTM C-579)	1,700 psi
Hardness (ASTM D-2240, Shore D)	100
Abrasion Resistance (ASTM D-4060, Taber Abrader CS-17 wheel)	0.05 gm max. weight loss
VOC Content (D-2369, Method E)	Primer 100 g/l Mortar 90 g/l
Cure Rate	24 hours (@77°F/25 °C)

Note: The above physical properties were measured in accordance with the referenced standards. Samples of the actual floor system, including binder and filler, were used as test specimens.

## COLOR

Crush is available in a broad color palette of aggregates. Virtually any color combination is possible. Natural aggregates can be used to create a wide range of color and design options. Contact your local Liquid Elements representative for design assistance.

## SUBSTRATE PREPARATION

Proper preparation is critical to ensure an adequate bond and system performance. The substrate must be dry and properly prepared utilizing mechanical methods. Questions regarding substrate preparation should be directed to your local Stonhard representative or Technical Service.

## RECOMMENDATIONS

- DO NOT attempt to install the material if the temperature of the Crush components is above 85°F/30°C. Higher temperatures will cause the material to harden more quickly than desired. Conversely, if the temperature of the components is 65°F/18°C or lower, Crush will be stiff and hard to apply. Do not use water or steam in the vicinity of the application. Moisture can seriously affect the working time and other properties.

- DO NOT attempt to install the material if the relative humidity is higher than 65%. Moisture will cause the material to cure quickly. If the humidity is too high, the material may set prior to being properly finished and could result in a sub-standard appearance.
- Application equipment must be cleaned immediately after use with scouring pads and warm, soapy water, or mineral spirits.
- Avoid contact with all liquid Parts A and B as they may cause skin and/or eye irritation.
- The use of safety glasses and impervious gloves is required during mixing and application.

## NOTES

- Detailed instructions on application and installation can be found in the Liquid Elements Installation Guide.
- Procedures for maintenance of the flooring system during operations are described in the Stonkleen Floor Cleaning Procedures Brochure.
- Specific information regarding chemical resistance is available in the Liquid Elements Chemical Resistance Guide.
- Safety Data Sheets for Crush are available on line at [www.liquidelements.com](http://www.liquidelements.com) under Tech Info or upon request.
- A staff of technical service engineers is available to assist with installation or to answer questions related to Liquid Elements' products.
- Requests for technical literature or service can be made through local sales representatives and offices, or corporate offices located worldwide.
- The appearance of all floor, wall and lining systems will change over time due to normal wear, abrasion, traffic and cleaning. Generally, high gloss coatings are subject to a reduction in gloss, while matte finish coatings can increase in gloss level under normal operating conditions.
- Surface texture of resinous flooring surfaces can change over time as a result of wear and surface contaminants. Surfaces should be cleaned regularly and deep cleaned periodically to ensure no contaminant build up occurs. Surfaces should be periodically inspected to ensure they are performing as expected and may require traction enhancing maintenance to ensure they continue to meet expectations for the particular area and conditions of use.



**Important:** Liquid Elements believes the information contained here to be true and accurate as of the date of publication. Liquid Elements makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.

Rev. 03/16 | © 2016 Liquid Elements

<b>Worldwide Offices:</b>	<b>USA</b> 877.642.7243	<b>Canada</b> 800.263.3112	<b>Mexico</b> (52)55.9140.4500	<b>South America</b> (54-3327)44.2222	<b>Europe</b> (32)2.720.8982	<b>Middle East</b> (971)4.3470460	<b>Africa</b> (27)11.254.5500	<b>Asia</b> (86)21.5466.5118
---------------------------	----------------------------	-------------------------------	-----------------------------------	--	---------------------------------	--------------------------------------	----------------------------------	---------------------------------